Application No.: 10/659888 Docket No.: AD6937USNA

Page 2

Amendments to Specification

On page 8 of the specification, line 25 to the end of the page, Table 1, Example 4 is amended as follows:

Table 1

Example	Wt	MATRIX	Wt.	RUBBER	WŁ.	Minerai	Filler/	Sample	Standard
No.	%		%		%	Filler	Rubber	Average	Deviation
							Ratio	IZOD	Izod
			ŀ				•	Ft-lib/in	Ft-lb/in (J/m)
								(J/m)	
Control	90	ß	10	Ç	0		0	9.5 (507)	0.4 (19)
1									
2	85	В	10	С	5	Α	0.5	9.1 (486)	0.5 (27)
3	80	В	10	С	10	Α	1.0	10.4 (555)	0.7 (39)
4	85	В	10	C	15	A	1.5	4.5 (240)	2.7 (143)
	<u>75</u>	1							